

Measurement Report

Sample name : Eskal15_3

User name : michael

Sample group : KSL

Time : 11/05/2017 at 09:42:36

Analysis parameters :

Measurement mode : 16 pict. / 11.25°

Heap diameter [mm] : 40

Upward velocity [mm/s] : 5

Rotational velocity [rpm] : 1

Calibration file : 20170509_145322.pdf

Powder information :

Volume [mL] : N/A

Weight [g] : N/A


Temperature [°C] : N/A

Hygrometry [%] : N/A

Number	Angle [°]	Cohesion	Height [mm]
1	55.05	1.28	22.71
2	54.17	0.86	22.71
3	52.65	0.57	22.71
4	51.79	0.3	22.71
5	51.53	0.43	22.71
6	52.04	0.67	22.71
7	52.41	0.79	22.71
8	52.16	0.78	22.71
9	51.91	0.61	22.71
10	52.41	0.56	22.71
11	53.25	0.73	22.71
12	54.17	0.99	22.71
13	55.05	1.5	22.71
14	55.69	1.87	22.71
15	55.48	1.96	22.71
16	55.05	1.68	22.71

Average	53.43	0.97	22.71
Deviation	1.44	0.51	0.00

First heap of powder



Operator notes : N/A

Date and signature of the operator :