

Measurement Report

Sample name : Eskal150_2

User name : michael

Sample group : Eskal

Time : 27/04/2018 at 13:25:13

Analysis parameters :

Measurement mode : 16 pict. / 11.25°

Heap diameter [mm] : 40

Upward velocity [mm/s] : 5

Rotational velocity [rpm] : 1

Calibration file : 20170509_145322.pdf

Powder information :

Volume [mL] : N/A

Weight [g] : N/A


Temperature [°C] : N/A

Hygrometry [%] : N/A

Number	Angle [°]	Cohesion	Height [mm]
1	33	0.29	11.18
2	33	0.29	11.18
3	32.77	0.27	11.18
4	33	0.31	11.18
5	33	0.31	11.18
6	33	0.31	11.18
7	33	0.31	11.18
8	33	0.3	11.18
9	33	0.3	11.18
10	33	0.3	11.18
11	33	0.3	11.18
12	33	0.3	11.18
13	33	0.29	11.18
14	33	0.29	11.18
15	33	0.29	11.18
16	33	0.29	11.18

Average	32.99	0.30	11.18
Deviation	0.06	0.01	0.00

First heap of powder



Operator notes : N/A

Date and signature of the operator :